

## AlumiBond

### Description

For use on virtually all roofs, walls, floors, gravity tanks, troughs, etc. UV stable and moisture tight, **AlumiBond** creates an air and vapor barrier. The thick 4 mil aluminum backing combined with **EternaBond's** advanced **MicroSealant™** creates a hard surface.

**AlumiBond** bonds to a wide range of materials including carbon steel, aluminum, galvanized steel, aluminum foil, gypsum board, wood, rubber, tar, polyethylene, polypropylene, polystyrene, fiberglass, brick, concrete, masonry, rubber, thermoplastics, single-ply roofing, etc. **AlumiBond** remains flexible to temperatures as low as -70° F making it virtually impossible to thermally shock the roof causing a leak.

### Duct Sealing Tape

2 mil high grade aluminum foil with a hybrid **EternaBond** Sealant. Fuses to rigid ductwork. Will never harden, crack or peel and fall off like other duct sealing products. Lasts as long as the ductwork!

### Basic Use

**AlumiBond** tape is designed for use on metal buildings, trailer/RV roofs and sides, drain pans, drain pipes, ductwork, boats, canoes, and as a protective coating for surfaces where abrasion and corrosion resistance is required. **AlumiBond** seals to itself so it can be cut and folded around an object.

### Composition

**AlumiBond** utilizes **EternaBond's** advanced **MicroSealant™ Technology**, a 100% solids formulation of synthetic resins, thermoplastics and non-curing rubber (non butyl) with a built-in primer. It is bonded to a 4-mil aluminum metal backing. The adhesive coating is protected by a silicone release liner, to be removed prior to application.

### Technical Data

Adhesion	>17 lbs/in width
Application temperature	150° F to -20° F ambient
Available widths	Up to 48"
Flexibility	1/2" radius @ -20°F
Flexibility temperature range	-70° F - >200° F
Shelf life	Up to 5 years
Sizes available	2", 4", 6", 12" x 50' rolls
Tensile strength	>1000 psi
Total thickness	20 mils (0.51 mm)
Weathering	Excellent resistance to wind, rain erosion, and ultra violet rays

Values are typical performance properties and characteristics based on laboratory testing. This is intended as a guide for comparison purposes and does not constitute a specification or specification range.

### Surface Preparation

Surface must be clean and dry. Moisture, dust, dirt or other foreign matter should be removed. Remove oil and grease, etc. with **EternaClean** or a non-residue cleaner such as acetone or lacquer thinner. Remove salt and other contaminants.

### Application

Install **AlumiBond** over the repair area, removing the release liner gradually to prevent contamination of the adhesive prior to application. Rub or roll with pressure using your hand or steel roller to activate bonding process. This material may be applied to clean dry surfaces from 150° F to -20° F ambient. Treat surface with **EternaPrime** for installations from 40° F to -20° F ambient.

**CAUTION:** All statements and technical information in this document are based on tests or data that ADCO believes is reliable. However, ADCO does not warrant or guarantee the accuracy or completeness of this information. The user has sole knowledge and control of factors that can affect the performance of ADCO's products in the user's intended application. It is the user's responsibility to conduct tests to determine the compatibility of ADCO's product with the design, structure, and materials of the user's end product and the suitability of ADCO's product for the user's method of application and intended use. The user assumes all risk and liability arising out of such use.

EternaBond AlumiBond 08/08/11

**ADCO Products, Inc**  
Michigan Center MI  
800.248.4010 phone  
517.764.0334 phone  
517.764.6697 fax  
[www.adcocorp.com](http://www.adcocorp.com)

**EternaBond, Inc.**  
Mundelein IL, USA  
888-336-2663 phone  
847-837-9449 fax  
[www.eter nabond.com](http://www.eter nabond.com)

---

**WARRANTY:** ADCO warrants its products to conform to ADCO's specifications at the time of sale when tested according to ADCO standards. If a product is proven to be defective when tested according to ADCO standards, ADCO will, at its option, refund the purchase price or replace or repair the defective product. THIS LIMITED WARRANTY IS THE BUYERS SOLE AND EXCLUSIVE REMEDY AGAINST ADCO AND IS IN LIEU OF ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. In no event shall ADCO be liable for any special, incidental, consequential, or punitive damages arising out of any claims whether based on negligence, contract, warranty, strict liability or otherwise.

