

WebSeal

Description

For use on virtually all roofs, **WebSeal** is designed to hold coatings, whether water or solvent based. **WebSeal** makes the roof water-tight prior to application of coating, creating a superior, faster method of waterproofing over conventional 3 course applications, eliminating dependence on the roof coating as a water barrier. **WebSeal** remains flexible to temperatures as low as -70° F making it virtually impossible to thermally shock the seam causing a leak.

WebSeal bonds to a wide range of surfaces including difficult roof materials such as EPDM, TPO, CSPE/Hypalon, most PVC, CPE, SBS, APP modifieds, asphalt BURs, coal tar BURs, plus all metal roofs, tiles, shingle, aluminum, galvanized steel, gypsum board, wood, polyethylene, propylene, polystyrene, fiberglass, brick, concrete, masonry, OSB, etc.

Basic Use

WebSeal tape is used to seal roof joints (seams) and tears, flashings, copings, skylights, gutters, etc. Perfect for repairing and restoring roofs on mobile homes and RVs. Extremely flexible, with no memory, so **WebSeal** conforms to virtually any shape without springing back. **WebSeal** seals to itself so it can be cut and folded around an object. A top coat of roof coating is necessary for UV protection.

Composition

WebSeal utilizes **EternaBond's** advanced **MicroSealant Technology**, a 100% solids formulation of synthetic resins, thermoplastics and non-curing rubber (non butyl) with a built-in primer. It is bonded to a woven polyester backing for maximum conformability. The adhesive coating is protected by a silicone release liner, to be removed prior to application.

Surface Preparation

Surface must be clean and dry. Moisture, dust, dirt or other foreign matter should be removed. Remove oil and grease, etc. with **EternaClean** or a non-residue cleaner such as acetone or lacquer thinner. Remove salt and other contaminants.

CAUTION: All statements and technical information in this document are based on tests or data that ADCO believes is reliable. However, ADCO does not warrant or guarantee the accuracy or completeness of this information. The user has sole knowledge and control of factors that can affect the performance of ADCO's products in the user's intended application. It is the user's responsibility to conduct tests to determine the compatibility of ADCO's product with the design, structure, and materials of the user's end product and the suitability of ADCO's product for the user's method of application and intended use. The user assumes all risk and liability arising out of such use.

| Technical Data | |
|--|---|
| Adhesion | 19 lbs/in width |
| Application temperature | 150° F to -20° F ambient |
| Available widths | Up to 48" |
| Elongation | >500% |
| Flexibility temperature range | -70° F - >200° F |
| Low temperature flexibility | 1/2" radius at -30° F |
| Pliability | No cracks in membrane |
| Shelf life | Up to 5 years |
| Standard roll size | 2", 4", 6", 8", 12", 24", 36" x 50' |
| Standard case quantity | 100 sq. ft. per case |
| Total thickness | 30 mils (1 mm) |
| Water vapor test (ASTME 96B) | .005 grms / 100" sq. / 24 hrs. / 100° F |
| Values are typical performance properties and characteristics based on laboratory testing. This is intended as a guide for comparison purposes and does not constitute a specification or specification range. | |

Application

Install **WebSeal** over the repair area, removing the release liner gradually to prevent contamination of the adhesive prior to application. Rub or roll with pressure using your hand or steel roller to activate bonding process. This material may be applied to clean dry surfaces from 150° F to -20° F ambient. Treat surface with **EternaPrime** for installations from 40° F to -20° F ambient. A topcoat of roofing coating is necessary for UV protection.

EternaBond WebSeal 08/24/11

ADCO Products, Inc
Michigan Center MI
800.248.4010 phone
517.764.0334 phone
517.764.6697 fax
www.adcocorp.com

EternaBond, Inc.
Mundelein IL, USA
888-336-2663 phone
847-837-9449 fax
www.eter nabond.com

WARRANTY: ADCO warrants its products to conform to ADCO's specifications at the time of sale when tested according to ADCO standards. If a product is proven to be defective when tested according to ADCO standards, ADCO will, at its option, refund the purchase price or replace or repair the defective product. THIS LIMITED WARRANTY IS THE BUYERS SOLE AND EXCLUSIVE REMEDY AGAINST ADCO AND IS IN LIEU OF ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. In no event shall ADCO be liable for any special, incidental, consequential, or punitive damages arising out of any claims whether based on negligence, contract, warranty, strict liability or otherwise.

